



Physical properties of TPX® DX310

Highly recommended for paper coating extrusion, possible use for fibre extrusion

Physical Properties	Item	Test Condition	Unit	Test Method	Value	
Basic Properties	Density		kg/m ³	ASTM-D1505	833	
	MFR	P=5kg, 260°C	g/10 min	ASTM-D1238	100	
	Melting Point	Peak Temp.	°C	JIS-K7121 (DSC method)	223	
	Water Absorption		%	ASTM-D570	<0.01	
Thermal Properties	Vicat Softening Point		°C	ASTM-D1525	147	
	Heat Distortion Temperature (HDT)	0.43 MPa	°C	ASTM-D648	80	
	Expansion Coefficient		10 ⁻⁶ K ⁻¹	ASTM-E831	1.17x10 ⁻⁴	
Mechanical Properties @ 23°C	Yield Stress		MPa	ASTM-D638	20	
	Tensile Strength		MPa	ASTM-D638	10	
	Elongation at Break		%	ASTM-D638	40	
	Tensile Modulus		MPa	ASTM-D638	820	
	Flexural Modulus		MPa	ASTM-D790	630	
	Flexural Strength		MPa	ASTM-D790	21	
	Izod Impact Strength	With Notch		J/m	ASTM-D256	25
		Without Notch		KJ/m ²	ASTM-D256	127
Rockwell Hardness	R Scale		-	ASTM-D785	42	
Optical Properties	Haze		%	ASTM-D1003	2.1	
	Transmittance		%	ASTM-D1003	93	
	Refractive Index		-	ASTM-D542	1.46	
Electrical Properties	Volume Resistivity		Ω . cm	ASTM-D257	>10 ¹⁶	
	Dielectric Breakdown Voltage		kV/mm	ASTM-D149	65	
	Dielectric Constant		-	ASTM-D150	2.1	

Notes:

MCI method 1 moulding temp: 310~330°C (depending on the grade)

MCI method 2 moulding temp: 260~280°C (depending on the grade)

All information and technical data are given as a guide only. Although every effort has been made to ensure that the information is correct, no warranty is given as to its completeness or accuracy.

Goodfellow Cambridge Limited
 Ermine Business Park
 Huntingdon, Cambridgeshire PE29 6WR
 Tel: +44 1480 424 800
 Fax: +44 1480 424 900
 Email: tpx@goodfellowusa.com
 Web: www.goodfellowusa.com